



# ULTRACRETE MANUFACTURING AND GLOBAL DISTRIBUTION



## ULTRACRETE-TX1000 ALL-IN-ONE TEXTURING OVERLAY MIX

### PHYSICAL STRENGTH PROPERTIES Architectural Specifications

<b><u>TESTS</u></b>	<b><u>METHOD</u></b>	<b><u>RESULTS</u></b>
Compression Strength	ASTM D695	5450 PSI
Splitting Tensile Strength	ASTM C496	629 PSI
Direct Tension (Pull Off Method)	ASTM C1583	Stronger than 6000 PSI Concrete (See Photo)
Drying Shrinkage	ASTM C596	No Effect



Testing Performed by Western Technologies, Inc., Phoenix, Arizona  
Consulting Engineers and Scientists

1-877-485-8721

[WWW.ULTRACRETE.COM](http://WWW.ULTRACRETE.COM)

EMAIL: [WWW.INFO@ULTRACRETE.COM](mailto:WWW.INFO@ULTRACRETE.COM)