



ULTRACRETE MANUFACTURING AND GLOBAL DISTRIBUTION



ULTRACRETE-TX1000 ALL-IN-ONE TEXTURING OVERLAY MIX

PHYSICAL STRENGTH PROPERTIES Architectural Specifications

| <u>TESTS</u> | <u>METHOD</u> | <u>RESULTS</u> |
|----------------------------|----------------------|-----------------------|
| Compression Strength | ASTM C109 | 5450 PSI |
| Splitting Tensile Strength | ASTM C496 | 629 PSI |
| Drying Shrinkage | ASTM C596 | No Effect |



Testing Performed by Western Technologies, Inc., Phoenix, Arizona
Consulting Engineers and Scientists
Updated Testing 9/26/11

1-877-485-8721
WWW.ULTRACRETE.COM
EMAIL: WWW.INFO@ULTRACRETE.COM